



Product Data Sheet AGM62MF0400

General Product Description

	Min	Max	Target
Carbon ASTM D5291	62		<input type="checkbox"/>
Sizing: EEA			<input type="checkbox"/>
Oxidized PAN Fiber: Milled			<input type="checkbox"/>
Oxidized PAN Fiber: Pan Based			<input type="checkbox"/>

Type: Oxidized PAN Fiber

Typical Analysis

(U.S. Standard Test Sieves)

Diameter, Microns	13
Fiber Density g/cm ³	1.37
Fib. Tensile Strength Gpa	0.21
Elongation @ Break %	26
Carbon ASTM D5291	62
Length (microns)	300

Test Methods

The PDS lists percentages which are only guaranteed following specific agreement between Asbury and the customer. They are listed here only to indicate approximate physical and chemical analysis. Purchasers should thoroughly test and independently verify satisfactory results before application. The user assumes the risk and liability for loss, damage, or injury arising from the application of the goods furnished.

UNCONTROLLED DOCUMENT: Prior to placing an order based on this PDS, contact the Asbury Sales Department to confirm that the information contained herein is current.

Revision Level: Revision 1

Revision Date:

1/6/2011

Asbury Graphite Mills, Inc.

PO Box 144 405 Old Main St.

Asbury, New Jersey 08802

Tel: (908) 537-2155 **Fax:** (908) 537-2108 **http://** www.asbury.com